



## Engineering Data

### Turcon<sup>®</sup> T29

#### Material

A high grade composition of virgin PTFE compounded with carbon fibre.

#### Colour

Grey.

The colour of the material may have variations in shading.

Property	Test Conditions	Standard	Unit	Typical Value
<b>General</b>				
Specific Gravity	23°C	ASTM D 792	g/cm <sup>3</sup>	<b>2.01</b>
Ball Indentation Hardness *)	23°C	ISO 2039-1	MPa	<b>39</b>
Shore D	23°C	ASTM D 2240	Shore D	<b>61</b>
<b>Mechanical</b>				
Tensile Stress @ Break	23°C	ASTM D 4894	MPa	<b>24</b>
Tensile Elongation @ Break	23°C	ASTM D 4894	%	<b>260</b>
Deformation under Load	23°C - 24h – 13.8 MPa	ASTM D 621	%	<b>4.9</b>
Creep	23°C-24h-13.8 MPa-1.5h	ASTM D 621	%	<b>3.1</b>
<b>Thermal</b>				
Coefficient of Linear Expansion	-75°C - +15°C	ASTM E 831	mm/mm/°K	<b>1E-4</b>
Coefficient of Linear Expansion	+15°C - +25°C	ASTM E 831	mm/mm/°K	<b>3E-4</b>
Coefficient of Linear Expansion	+25°C - +125°C	ASTM E 831	mm/mm/°K	<b>2E-4</b>
<b>Miscellaneous</b>				
Surface Resistivity	23°C	DIN 53482	Ohm	<b>6E+4</b>
Volume Resistivity	23°C	DIN 53482	Ohm x cm	<b>1E+4</b>

\*) Only used in Europe

Reg. No. T29 Version 3, 2015-10-26

- ® Registered Trademark of Trelleborg Sealing Solutions Helsingør (Trelleborg Sealing Solutions Denmark A/S).
- ® The turquoise colour is a Registered Trademark for products of Trelleborg Sealing Solutions.
- © Copyright 2006 - Trelleborg Sealing Solutions Helsingør.

This is an uncontrolled copy of the Trelleborg Sealing Solutions Helsingør Engineering Data.

Trelleborg Sealing Solutions Helsingør assumes no responsibility for performance, expressed or implied, and warranty is limited to replacement of product for defects in material and workmanship.

Based upon our ongoing seals and materials development programme, Trelleborg Sealing Solutions Helsingør reserve the right to change properties contained within this Engineering Data sheet, in the light of experience, without further notice.

Trelleborg Sealing Solutions Helsingør  
P.O. Box 310, Fabriksvej 17, DK-3000 Helsingør, Denmark  
Phone+45 4927 0333 Fax+4922 5209 www.trelleborg.com